



## Technical data

Substance	
Fleece	Polypropylene
Membrane	Polyethylene copolymer
Reinforcement	Polypropylene non-woven fabric

  

Attribute	Regulation	Value
Colour		white-transparent
Surface weight	BS EN 1849-2	110 ±15 g/m <sup>2</sup>
Thickness	BS EN 1849-2	0.40 ±0.1 mm
Water vapour resistance factor $\mu$	BS EN 1931	18 750
sd-value	BS EN 1931	7.50 ±0.25 m
sd-value humidity variable	BS EN ISO 12572	0.25 - >25 m
g-value		37.50 ±1.25 MN-s/g
g-value humidity variable		1.25 - >125 MN-s/g
Reaction to fire	BS EN 13501-1	E
Tensile strength MD/CD	BS EN 13859-1	350 N/5 cm / 290 N/5 cm
Elongation MD/CD	BS EN 13859-1	15 % / 15 %
Nail tear resistance MD/CD	BS EN 13859-1	200 N / 200 N
Artificial ageing by long term	BS EN 1296 / BS EN 1931	passed
Temperature resistance		-40 °C to 80 °C ; -40 °F to 176 °F
Thermal conductivity		0.17 W/(m·K)
Airtightness	BS EN 12114	tested
National technical approval (DE)	DIN 68800-2	Z-9.1-853
CE labelling	BS EN 13984	available

## Area of application

Can be used as a vapour check and airtightness membranes for all externally diffusion-open structures, e.g. with roof underlay (pro clima SOLITEX), softwood fibreboard or MDF board. For a high level of protection against moisture induced failures in structurally challenging constructions such as diffusion-resistant flat/pitched roofs. Also suitable in extreme environments such as in high mountain regions. Further information is given in the study "Calculating potential freedom from structural damage of thermal insulation structures in timber-built and steel systems"

## Forms of delivery

Art. no.	GTIN	Length	Width	Folded	Contents	Weight	PU	Container
10076	4026639011992	50 m	3 m		150 m <sup>2</sup>	18 kg	1	20
10092	4026639011244	50 m	1.5 m		75 m <sup>2</sup>	9 kg	1	20
10093	4026639011237	20 m	1.5 m		30 m <sup>2</sup>	4 kg	1	42
12222	4026639122223	50 m	3 m		150 m <sup>2</sup>	18 kg	1	20

## Advantages

- ✓ Maximum protection for the insulation
- ✓ Ideal prevention against structural damage and mould, even in the event of unexpected moisture intrusion
- ✓ Extremely high moisture-variable diffusion resistance in any climate spanning a very wide range (more than 100 x; g-value: 1.25 MN-s/g up to > 125 MN-s/g)
- ✓ High diffusion resistance in a winter climate
- ✓ g-value = 1.25 MN-s/g back-diffusion capacity in summer
- ✓ Very low coefficient of expansion when combined with spray insulation materials
- ✓ Lowest VOC rating in hazardous substance test

The information provided here is based on practical experience and the current state of knowledge. We reserve the right to make changes to the recommended designs and processing or to make alterations due to technical developments and associated improvements in the quality of our products. We would be happy to inform you of the current technical state of the art at the time you use our products.

Further information about application and construction is given in the pro clima planning documentation and application recommendations. If you have any questions, please call the pro clima technical hotline Ireland and UK:  
 Phone: +353 46 9432104  
 Fax: +353 46 9432435  
[info@ecologicalbuildingsystems.com](mailto:info@ecologicalbuildingsystems.com)

**For Stockists contact**  
**Ireland**  
 T. 046 9432104  
 F. 046 9432435  
**UK**  
 T. 01228 711 511  
 F. 01228 712 280

**Ecological Building Systems**  
[info@ecologicalbuildingsystems.com](mailto:info@ecologicalbuildingsystems.com)

[www.ecologicalbuildingsystems.com](http://www.ecologicalbuildingsystems.com)



## General conditions

pro clima INTELLO PLUS should be laid with the side with the plastic film (the printed side) facing the installer. They can be laid flat either at right angles to or along the sub-structure (such as the rafters) without sagging. If laid horizontally (at right angles to the sub-structure) then the maximum space permitted between the rafters is 100 cm. After laying, it is necessary to support the weight of the insulation with lathing on the inside. The laths should be no more than 50 cm apart. If, when using insulation mats and boards, for example, you expect systematic tension as a result of the insulation weight on the adhesive tape joins, an additional supporting lath should be placed on the overlap. Alternatively, the adhesive tape can be reinforced along the overlap by sticking strips of adhesive tape at right angles to the overlap every 30 cm.

Airtight seals can only be achieved on vapour control membranes that have been laid without folds or creases. Ventilate regularly to prevent excessive humidity (e.g. during the construction phase). Occasional rush/inrush ventilation is not adequate to quickly evacuate large amounts of construction-related humidity from the building. Use a dryer if necessary.

To prevent condensation, INTELLO PLUS should be stuck down so that it is airtight immediately after installing the thermal insulation. This particularly applies when working in winter.

Additionally for injected foam insulation

INTELLO PLUS can also be used as a membrane for all types of injected foam insulation. Your reinforcing layer prevents stretching during injection of the insulation foam. If laid along the sub-structure it has the advantage that the overlap is supported on a firm foundation and is therefore protected.

To prevent condensation, the injected foam insulation should be introduced immediately after installing the airproofing layer. This particularly applies when working in winter.



Feuchtevariable Dampf-  
bremsbahn INTELLO zur  
Verwendung entsprechend  
DIN 68800-2:2012-02



\* Information sur le niveau d'émission de substances volatiles dans l'air intérieur, présentant un risque de toxicité par inhalation, sur une échelle de classe allant de A+ (très faibles émissions) à C (fortes émissions)



The information provided here is based on practical experience and the current state of knowledge. We reserve the right to make changes to the recommended designs and processing or to make alterations due to technical developments and associated improvements in the quality of our products. We would be happy to inform you of the current technical state of the art at the time you use our products.

Further information about application and construction is given in the pro clima planning documentation and application recommendations. If you have any questions, please call the pro clima technical hotline Ireland and UK:  
Phone: +353 46 9432104  
Fax: +353 46 9432435  
info@ecologicalbuildingsystems.com

For Stockists contact  
Ireland  
T. 046 9432104  
F. 046 9432435  
UK  
T. 01228 711 511  
F. 01228 712 280

Ecological Building Systems  
info@ecologicalbuildingsystems.com

www.ecologicalbuildingsystems.com

